



TECHNICAL SPECIFICATION CUSH 'N' WOOD

- APT CRUMB
- DESIGNED FOR USE UNDER WOODEN FLOORS
- UNIQUE MOISTURE LOCK SYSTEM
- IMPACT SOUND REDUCTION PROPERTIES

RECOMMENDED AREAS OF USE

SUITABLE FOR SOLID AND LAMINATE WOOD FLOORS. SUPPORTS FLOORS GIVING A MORE COMFORTABLE FEEL

STANDARD SPECIFICATIONS

TOP SURFACE	Spun bonded polypropylene	
BOTTOM SURFACE	Brown thermoplastic film	
NOMINAL THICKNESS	4.00 mm	
NOMINAL ROLL WEIGHT	11 Kg	24.2 lb
WEIGHT PER UNIT AREA	730 g/m	
ROLL LENGTH	11.0 m	36.0 ft
ROLL WIDTH	1.37 m	54 in
GUARANTEE	Lifetime of the initial installation	

BS. 5808 : 1991 TEST RESULTS - BRITISH STANDARD FOR UNDERLAYS

THERMAL RESISTANCE (TOG RATING)	BS.4745	1.1 TOG
IMPACT SOUND IMPROVEMENT INDEX		25 dB
HOT METAL NUT TEST	BS.4790	Pass - Medium radius of effect
KLIENBRENNER	DIN 54332	Pass - Burning Class T-a
END USE CLASSIFICATION	BS.5808	N/A
WORK OF COMPRESSION AFTER 1000 IMPACTS	BS.4098	73 J/m
RETENTION OF WORK OF COMPRESSION	BS.4098	>90 %
LOSS IN THICKNESS AFTER STATIC LOADING	BS.4939	<5.00 %
LOSS IN THICKNESS AFTER DYNAMIC LOADING	BS.4052	<5.00 %
RESISTANCE TO CRACKING	BS.5808 (A)	Pass

Please note: This document does not constitute a manufacturing specification. It details important technical performance and physical characteristics of the product only. Please contact the Technical Department for any further information.

Carpets Direct (GB) Ltd Unit 3 Riverside Works Reservoir Road Hull HU6 7QD
Tel: +44(0)1482 215008 Web: www.MrCarpetUnderlay.co.uk

