

Heatflow Wood & Laminate



High density sponge rubber underlay for laminate and solid wood floors installed over underfloor heating

Incorporates Thermylin™ for improved thermal conductivity

For use under floating laminate, solid timber and engineered wooden floors

Suitable for both domestic and contract applications

Guaranteed for the serviceable lifetime of the floorcovering under which it is laid when used in the recommended locations

Roll size: 1.37 m x 11.0 m

Note: When fitted over a concrete subfloor, ensure that a moisture membrane of a grade recommended by the manufacturers of the wood or laminate flooring is installed between the subfloor and Heatflow Wood & Laminate underlay

Specification	Result	Method
Nominal weight Nominal Roll Weight	2407 g/m ² (71 oz/yd ²) 74 lbs	
Nominal thickness	2.75 mm	BS 4051
Mean original thickness from nominal thickness	2.0 %	
Difference between maximum & minimum original thicknesses	0.3 mm	
Tensile strength - length	1100 kPa	EN ISO 1798: 2000
Tensile strength - width	500 kPa	
Elongation @ break - length	60 %	
Elongation @ break - width	40 %	
Compressive stress @ 25% strain	70 kPa	EN ISO 3386 Pt 2: 1998
Compressive stress @ 50% strain	400 kPa	
Odour	No objectionable odour	
Colour and appearance	Black sponge rubber sheet with printed Textron paper backing	
Weighted reduction in impact sound pressure level (ΔL_w)	21 dB	Tested to BSEN ISO 140-8: 1998, rated to BSEN ISO 717-2: 1997.
Thermal properties		
Thermal resistance	0.35 togs	BS 4745
R-Value	0.035 m ² K/W	
U-Value	28.6 W/m ² K	
Thermal conductivity	0.101 W/m.K	
Flammability	Low Radius of effects of ignition	BS 4790/5287

Please note: This document does not constitute a manufacturing specification. It details important technical performance and physical characteristics of the product only. Please contact the Technical Department for any further information.

Mr Carpet Underlay



SAVING THE WORLD FROM HIGH PRICES

