



# TECHNICAL SPECIFICATION

## Dreamwalk

### High quality polyurethane rebond carpet underlay

Suitable for stretch-fit installation of carpets

End Use Classification (BS 5808: 1991): L/U, Luxury Use

Excellent thermal insulation

High degree of impact sound insulation

Guaranteed for 25 years or the serviceable lifetime of the carpet when used in the recommended locations

Roll size: 15sq.m of 1.37 m x 11.0 m

Specification	BS Requirements	Result	Method
Nominal square weight		1210 g/m <sup>2</sup>	
Nominal density		110 kg/m <sup>3</sup>	
Nominal roll weight		39 lbs	
Nominal thickness		11.00 mm	BS 4051
Mean original thickness from nominal thickness	Maximum 12%	2.2 %	
Difference between max. & min. original thicknesses	Maximum 3mm	0.3 mm	
Work of compression	Minimum 50 J/m <sup>2</sup> after dynamic loading for 1000 impacts	195 J/m <sup>2</sup>	BS 4098 & BS 4052
Compression after dynamic loading	Minimum 2mm, maximum 7mm after 1000 impacts	6.5 mm	
Retention of work of compression	Minimum 40% of original after 1000 impacts	91 %	
Breaking strength - length	Minimum 40N	125 N	BS 2576
Breaking strength - width		100 N	
Extension under force - length	Maximum 10% @ 40N	4.4 %	
Extension under force - width		1.8 %	
Loss in thickness after dynamic loading	Maximum 15% after 1000 impacts	3.8 %	BS 4052
Loss in thickness after static loading	Maximum 15% after 24hrs loading & recovery	4.6 %	BS 4939
Resistance to cracking	Not greater than 50mm	Pass	BS 5808
Odour		No objectionable odour	
Colour and appearance		Blue Facing with printed paper backing	
<b>Flammability</b>	<b>Notes</b>	<b>Result</b>	<b>Method</b>
Hot metal nut test	Tested in Interfloor laboratory	Low radius of effects of ignition	BS 4790 & BS 5287
<b>Thermal Properties</b>			
Thermal resistance		2.9 togs	BS 4745
<b>Acoustic Properties</b>			
Weighted reduction in impact sound pressure level (Delta Lw)		46 dB	BSEN ISO 140-8: 1998 and BSEN ISO 717-2: 1997

Please note: This document does not constitute a manufacturing specification. It details important technical performance and physical characteristics of the product only. Please contact the Technical Department for any further information.

Carpets Direct (GB) Ltd Unit 3 Riverside Works Reservoir Road Hull HU6 7QD

Tel: +44(0)1482 215008 Web: [www.MrCarpetUnderlay.co.uk](http://www.MrCarpetUnderlay.co.uk)

